

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

BNSDOCID: <WO 9855162A2 | >

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

-1-

TREATING METAL SURFACES TO ENHANCE BIO-COMPATIBILITY AND/OR PHYSICAL CHARACTERISTICS

Field of the invention

5

The present invention relates to a method of treating metal surfaces to enhance the bio-compatibility and/or physical characteristics of said surfaces. The invention also relates to bio-compatible metal articles. The invention is particularly relevant to surfaces of medical devices.

10

Introduction

15

20

Many medical techniques are known in which human or animal blood is brought into contact with foreign surfaces, either within the body or outside the body. In some situations, usually due to mechanical characteristics, it is necessary to use metallic surfaces, as required by coronary stents (vascular endoprotheses) located within arteries or, for example, within heat exchanger assemblies external to the body. Thus, in the first application, the mechanical strength of the metal object is required whereas in the external application it is the heat transfer characteristics that are required. However, in both applications, blood or related blood products are brought into contact with metal surfaces, which may in turn have detrimental effects upon the blood itself.

25

30

When presented to foreign surfaces, blood has a tendency to clot. It is known that blood activation in response to contact with a foreign surface occurs by the intrinsic pathway (see Figure 2 of Johan Riesenfeld *et al*, *Surface Modification with Functionally Active Heparin*, Medical Device Technology, March 1995 pages 24-31, the disclosure of which is incorporated herein by reference), triggered by the conversion of Hageman (F)XII to an active enzyme, FXIIa. This then initiates the sequential activation of coagulation factors FXI, FIX and FX and finally FXa converts prothrombin into enzymatically active thrombin, which precipitates the soluble plasma protein fibrinogen into a solid fibrin clot. The coagulation system is under the control of a series of

-2-

regulatory mechanisms in the blood and the vascular wall, the most important being the plasma coagulation inhibitor, antithrombin (III).

Heparin is a naturally occurring substance which consists of a polysaccharide with a heterogeneous structure and a molecular weight ranging from approximately 6000 to 30000 Dalton (atomic mass units). It prevents uncontrolled clotting by suppressing the activity of the coagulation system through complexing with antithrombin (III), whose activity it powerfully enhances. Approximately one in three heparin molecules contains a sequence of highly specific structures to which antithrombin binds with high affinity. When bound to the specific sequence, the coagulation enzymes are inhibited at a rate that is several order of magnitude higher than in the absence of Heparin. Thus, the heparin molecule is not in itself an inhibitor but acts as a catalyst for natural control mechanisms without being consumed during the anticoagulation process. The catalytic nature of heparin is a desirable property for the creation of a bio-active surface, because the immobilised heparin is not functionally exhausted during exposure to blood but remains a stable active catalyst on the surface.

A method for making nonthrombogenic surfaces is disclosed in United States Patent No. 3,634,123. A method for reducing thrombosis of blood, induced by contact with foreign surfaces, is shown in which the surface are treated with a cationic surface active agent and a conventional anticoagulant such as heparin. The technique disclosed in this patent is appropriate for plastic surfaces but cannot be extended to metal surfaces.

The Benestent II Group at the Department of Cardiology, University Hospital Rotterdam have developed a heparin coated Palmaz-Schatz stent, in which an end point of the heparin molecule is covalently coupled to an underlying polymer matrix, similar to the type manufactured under the trade mark Carmeda Bioactive Surface by CBAS Carmeda Inc, Sweden. The process consists of four stages:

- etch the metal surface
- introduce a poly-amino layer which is ionically attached to the surface

-3-

- covalently bond the functional amino groups to the aldehyde groups of partially degraded heparin molecules
- chemically stabilise the bonded heparin by use of a reducing agent.

5 An advantage of this known approach is that it allows heparin molecules to be attached to the poly-amino layer in a relatively friendly chemical environment. However, the poly-amino layer is only physically attached to the conditioned metal surface and as such the strength of the attachment is somewhat dubious. Thus, in continuous use within the body, there is a risk of heparin or similar molecules becoming detached thereby reducing the effectiveness of the stent which in turn may require further surgery. Similarly, in external applications, the effectiveness of the device may degrade and this degradation may be accelerated if the device has to be cleaned under particularly harsh conditions. Finally anti-coagulant coating methods generally incur relatively high manufacturing costs.

15 US-A-5356433 discloses the treatment of a stent or other medical device by the alleged formation of covalent linkages between a biologically active agent and a metallic surface. In one example tantalum stents were primed with a solution in ethanol of *N*-(2-aminoethyl-3-aminopropyl)trimethoxysilane so that a bond was formed between the tantalum oxide layer on the surface of the stents and the silicon of the silane on curing at 20 110°C. Heparin is then coupled to the amino groups using 1,3-ethyldimethyl-aminopropyl carbodiimide (EDC). In a second example, an ethanolic solution of an amiofunctional polymeric silane, trimethylsilylpropyl substituted polyethyleneimine is bonded to the surface of tantalum stents, also with curing at 110°C, after which heparin was coupled to the coating using EDC. Other examples use stainless steel wire, platinum tungsten wire 25 and aminopropyl-trimethoxysilane as primer. However, priming has to be carried out with heating. The present applicants consider that covalent bonds to the metal surface are not formed under the conditions described because the water which is inevitably present in the ethanol hydrolyses the linkages between the methoxy groups and silicon and because the reaction between the trimethoxysilane groups and surface oxide requires a catalyst which 30 is absent. Furthermore, the heparin is coupled to the priming layer directly and not by polymeric or oligomeric spacer arms, is not sterically available, and will therefore not

-4-

exhibit its full anti-coagulant activity. US Patent 5607475 reports that the use of aminosilanes in coatings on metal or glass surfaces has not been good at producing a surface with a high level of both bio-effectiveness and stability.

5 US-A-5607475 discloses an endoprosthesis having a metal surface for contact with body fluids, the metal surface having a coating thereon comprising:

(a) a silane which includes a vinyl functionality, the silane being adherent to the metal surface so that the vinyl functionality is pendant from the surface;

10 (b) a graft polymer, the graft polymer being covalently bonded with the pendant vinyl functionality of the adherent silane, the graft polymer simultaneously formed and bonded to the pendant vinyl functionality by free radical reaction initiated by an oxidising metal with at least one ethylenically unsaturated monomer selected from the group consisting of acrylamide and acrylic acid;

15 (c) a polyamine spacer covalently attached to the graft polymer; and

(d) a biomolecule covalently attached to the spacer.

The preferred primer is trichlorovinylsilane which is applied in xylene. However, under these conditions, the primer is merely physically held to the metal surface and does not
20 form a chemical bond with oxide on the metallic surface. The procedure for subsequent attachment of heparin is lengthy and complex. The method described is neither effective nor practical, and the information and belief of the present applicants is that it has not been put into practice.

25 WO 97/07834 acknowledges that in order to obtain truly anti-thrombogenic surfaces, proper immobilisation of the biomolecules is the key and that the binding of a base or primer layer to metal or glass surfaces presents a problem because of the difficulty of forming covalent bonds to the surface. The priming step uses trichlorovinylsilane in xylene and therefore does not form a covalent attachment with the metal surface, and
30 subsequent attachment of heparin is by an elaborate multi-step procedure.

-5-

Summary of the Invention

The invention is concerned with the problem of providing a primer layer on a metal, glass or ceramics surface which is sufficiently durably attached that it can withstand prolonged contact with blood or other biological fluids, that enables bio-compatible hydrophilic chains or spacer arms to be grafted onto the primer layer, and that allows easy and effective attachment of heparin or other biologically active molecules.

In one aspect, the present invention provides a method of treating a metal, glass or ceramics article having at its surface oxide or hydroxide to enhance the bio-compatibility and/or physical characteristics of the surface, said method comprising the steps of

priming said surface in an aprotic organic solvent (i.e. a solvent which substantially does not contain water and is free of -OH groups) by means of functional molecules each of has at least one alkoxysilane group or alkoxyalkylsilane group which forms at least one covalent bond by reaction with the oxide or hydroxide of said surface and a catalyst which brings about said bond formation, said functional molecules having at least one other group which can participate in graft polymerisation; and

effecting graft polymerisation from said functional molecules to build bio-compatible and/or hydrophilic polymer chains. The graft polymerisation is preferably a free radical polymerisation because of ease of production on a commercial scale and because of speed of the reaction. However, it could be an addition polymerisation which is ionically initiated.


In the presence of an acid catalyst, priming can be carried out under mild conditions, and thereafter formation of spacer arms and attachment of heparin or other biomolecules (if required) can be carried out under mild aqueous conditions. Attachment of heparin or other biological macromolecules may be carried out simultaneously with formation of the spacer arms, or the spacer arms may be provided with attachment sites for heparin or other biological molecules as they are formed, after which the heparin or other biological macromolecules are attached in a separate operation.

-6-

According to a second aspect of the present invention, there is provided a bio-compatible metal article comprising functional molecules covalently bonded to the surface of said article and bio-compatible polymer chains covalently bonded to said functional molecules.

Description of preferred features

Where they are monomeric, said functional molecules may be of any of the formulae:



wherein R^1 represents a hydrogen atom or an alkyl group, R^2 , R^3 and R^4 represent an alkyl group and n is 0 or is a positive integer. In the above molecules, preferably R^1 represents hydrogen, methyl or ethyl and R^2 , R^3 and R^4 represent methyl or ethyl and the value of n is from 0 to 6. Other values of R^3 and R^4 e.g. hydroxyl or chloride are possible provided that the bond formation is not interfered with.

Preferably said vinylfunctional silane molecules are oligomers or polymers, and preferably said vinylfunctional silane molecules become bonded to said surface at a plurality of locations.

In a preferred group of oligomers or polymers, the functional molecules comprise a $[-\text{Si}-\text{O}-]_n$ chain having alkoxy groups directly attached to the silicon atoms and having olefinically unsaturated groups attached directly or via linking groups to the silicon atoms. Preferably the functional molecules have vinyl and alkoxy groups attached to the silicon atoms of the chain.

-7-

The molecules of a further preferred group of functional molecules have:

an oligomeric or polymeric chain based on carbon atoms, which chain may also include nitrogen or oxygen atoms;

one or more alkoxy silane or alkylalkoxy silane groups attached to the chain for forming covalent bonds with oxide or hydroxide of the surface; and

one or more olefinically unsaturated groups which can participate in free radical polymerisation. The above functional molecules preferably have trialkoxy silane or dialkoxyalkyl silane groups, alkyl preferably being methyl or ethyl.

Particular functional molecules which may be used include one or more of:

3-(trimethoxysilyl) propyl methacrylate;

vinylmethoxysiloxane oligomer;

diethoxymethylsilyl-modified polybutadiene

triethoxysilyl-modified polybutadiene.

The graft polymerisation preferably involves free-radical polymerisation including polymerising a plurality of types of polymerisable molecules to form said polymer chains. In a further preferred embodiment, at least one type of said polymerisable molecules is suitable for additionally bonding to a bio-active molecule. In an alternative embodiment at least one of said polymerisable molecules is a modified bio-active molecule. In a further preferred embodiment, said bio-active molecule is heparin, or in the case of a modified bio-active molecule, a heparin derived molecule.

In a further preferred embodiment, said metal surface is a surface of a medical device.

Brief Description of the Drawings

Figure 1 shows an overview for the treatment of a metallic device including a functionalisation step and a polymerisation step.

Figure 2 details the functionalisation step identified in Figure 1.

-8-

Figure 3 details a process for performing the polymerisation step identified in Figure 1.

Figure 4 details an alternative process for carrying out the polymerisation step identified in Figure 1.

5 Figure 5 illustrates a typical metal surface to be treated in accordance with the present invention.

Figure 6 details a suitable functional molecule, a vinylfunctional silane molecule, to be reacted with the metal surface illustrated in Figure 5.

10 Figure 7 illustrates the silane molecule detailed in Figure 6 covalently bonded to the metal surface illustrated in Figure 5.

Figure 8 details a suitable vinyl monomer for free radical polymerisation, said monomer being acrylamide.

Figure 9 details a second vinyl monomer suitable for bonding to a bio-active molecule, said monomer being known as 3-aminopropyl methacrylamide.

15 Figure 10 details the chemical structure, following polymerisation, of the functionalised metallic surface shown in Figure 7, wherein polymerisation has been effected using acrylamide detailed in Figure 8 and 3-aminopropyl methacrylamide detailed in Figure 9.

20 Figure 11 details the chemical structure of a repeating unit of a heparin molecule, said molecule being desirable so as to further enhance blood-compatibility of the polymer chains shown in Figure 10.

Figure 12 details a metallic surface such as shown in Figure 10, wherein said surface has been further treated with heparin.

25 Figure 13 generally illustrates a metallic surface with polymer chains as detailed in Figure 12, interacting with antithrombin (III).

Figure 14 details the interaction of antithrombin (III) with blood clotting factors so as to prevent formation of fibrin and hence blood clots.

Figure 15(a) details a molecule of modified heparin.

30 Figure 15(b) further details the molecule shown in Figure 15(a), which may be reacted in conjunction with a vinyl monomer such as shown in Figure 8, with a functionalised surface such as shown in Figure 7, to produce substantially the polymerised

-9-

surface shown in Figure 12.

Figures 16(a) to 16(c) show typical metal medical devices that may be treated in accordance with the present invention.

5 Figs 17(a) and 17 (b) are SEM micrographs (x 800) showing respectively cell and fibrin deposition on untreated stainless steel and lack of cell and fibrin deposition onto heparin-treated stainless steel according to the invention.

Detailed Description of the Preferred Embodiments

10 The invention will now be described by way of example only with reference to the previously identified drawings.

An overview of the method of treating a metal surface to enhance its bio-compatibility with for example blood or blood related products is shown in Figure 1. A metal surface of an article such as a medical device is particularly suitable for treating in accordance with the method shown. Typical medical devices include heat exchangers for dissipating heat in blood, coronary stents and peripheral stents (vascular endoprotheses), guide wires as used in percutaneous transluminal coronary angioplasty (PTCA), artificial heart valves and devices for storage and/or transfer of biological material such as blood or blood related products. Initially a metal article or device, is taken from store at step 101, whereafter at step 102 suitable chemicals for functionalising the device surface are selected. These chemicals include a functional molecule, a solvent and a catalyst. As indicated a suitable functional molecule is a vinylfunctional silane. At step 103 the surface of the metallic article is functionalised or primed, that is, treated with the chemicals selected at step 102. Following functionalisation, at step 104 suitable materials for polymerising on the metallic surface are selected after which polymerisation is carried out at the primed surface to form blood-compatible polymer chains, as indicated at step 105. Following polymerisation at step 105, the device with its functionalised and polymerised surface may be stored, as indicated at step 10, and subsequently used as indicated at step 107.

15
20
25
30

-10-

Step 103 for priming or functionalising a given metallic device is detailed in Figure 2. At step 201, the surface or surfaces of a given metallic device are cleaned. For the example of a stainless steel surface, this step would typically involve placing the device in 1% w/v sodium bicarbonate solution at 60° centigrade for one hour. For other metallic surfaces, either a sodium bicarbonate solution as described or another suitable solution may be used. Furthermore for metallic devices wherein an internal surface is to be functionalised, such as for example a heat exchanger, the cleaning solution may be passed through the internal mechanism of the device, for example by pumping said solution through said device using a peristaltic pump and appropriate connection tubes. At step 202 the metallic device is washed with hot water whereafter it is dried, preferably at room temperature, as indicated at step 203. At step 204 the functionalisation chemicals selected at step 102 in Figure 1, are prepared. The preparation involves, for example, mixing the vinylfunctional silane in a suitable solvent together with a small amount of added catalyst. Typically for stainless steel surfaces a suitable vinylfunctional silane is vinylmethoxysiloxane oligomer, a suitable solvent is toluene and a suitable catalyst is a few drops of dilute acetic acid. At step 205 the device is placed in the prepared mixture of functionalisation chemicals for a desired length of time. In Figure 2 the length of time is indicated as two hours and a suitable temperature is room temperature. The temperature and length of time may be varied according to the degree of functionalisation required. Thus, leaving the device in the functionalisation solution for merely one hour will provide the required functionalisation for certain applications. Similarly the temperature may be varied to effect the rate of functionalisation. At step 206 the functionalised device, having been removed from the functionalisation solution, is washed. Typically the device is washed in an organic solvent such as methanol. At step 207 the device is washed with water to remove any undesirable chemicals remaining.

Step 105 for polymerisation with bio-compatible polymer chains at a previously primed metallic surface, may be performed in various ways. A first method for polymerising a given metallic device is detailed in Figure 3. This step follows step 104 in Figure 1 wherein the required polymerisation materials have been selected. At step 301 the polymerisation mixture is prepared and as indicated in this method a suitable bio-active

-11-

molecule such as modified heparin is incorporated in this step. The heparin selected is a modified version in which the heparin molecules are provided with means for attachment to a polymer chain. Typically the modified heparin or other bio-active molecule, is mixed with a further polymerisable molecule or molecules. Suitable polymerisable molecules which may be attached to the heparin are polymerisable vinyl monomers, for example acrylamide. The selected polymerisable molecules are then mixed with a small amount of free radical indicator such as sodium thiosulphate and a small amount of ammonium persulphate. Typically the mixture is used at room temperature for a period of about three hours, although it is again a matter of specific requirements regarding the exact temperature and time used. Following polymerisation at step 302, the polymerised metallic device surface is washed with water, as indicated at step 303.

An alternative method for forming polymer at a primed surface of a metal article step 105 in Figure 1, is detailed in Figure 4. At step 401 a suitable polymerisable mixture is prepared. The mixture prepared at step 401 does not incorporate a bio-active molecule, and suitable polymerisable molecules are for example acrylamide and 3-aminopropyl methacrylamide prepared in an aqueous medium along with a small amount of sodium thiosulphate ($\text{Na}_2\text{S}_2\text{O}_3$) and a small amount of ammonium persulphate ($\text{NH}_4\text{S}_2\text{O}_8$). At step 402 the metallic device is treated with the prepared polymerisation mixture. The treatment conditions again may vary depending on requirements, but typically three hours at room temperature would be suitable for many medical devices. Following step 402 the metallic device is washed with water at step 403 whereafter at step 404 suitable bio-activation chemicals including for example commercially available unmodified heparin, are prepared. In the case of unmodified heparin, preparation involves dissolving the heparin in water in admixture with a suitable solvent, for example 1-ethyl-3-(3-dimethyl amino propyl) carbodimide hydrochloride. At step 405 the polymerised metallic device is placed in the bio-activation mixture, again for a required time and at a required temperature as appropriate. Typically room temperature for a period of six hours is found to be suitable for many medical applications. Following step 405, the polymerised metallic device with incorporated bio-active molecules is washed with water, as indicated at step 406.

The two methods of polymer formation at a primed surface of a metal article,

-12-

generally illustrated in Figures 3 and 4 respectively, do not necessarily have to lead to incorporation of bio-active molecules. For example simple polymerisation from a functionalised metal surface, using for example acrylamide, provides hydrophilic polymer chains from said functionalised surface. In general such hydrophilic polymer chains provide a degree of improved bio-compatibility of a given metal surface with biological materials such as blood or blood related products. This is because hydrophilicity is related to lubricity of the surface and thus said surface may be physically more slippery which in itself provides an improved degree of compatibility with certain biological materials. However, incorporation of certain bio-active molecules, e.g. heparin, hirudin or prostaglandin for example, further improves the bio-compatibility (blood-compatibility) of a given metal surface. The term polymerisable molecule generally refers to a material suitable for building a given polymer chain. As indicated above one or more polymerisable molecules may be used, for example acrylamide being used alone or acrylamide being used alongside modified heparin during polymerisation or alongside a further non bio-active molecule such as 3-aminopropyl methacrylamide, which provides suitable bonding sites for incorporation of a bio-active molecule.

Figures 1 to 4, as described, detail two methods of treating a metal surface to enhance the bio-compatibility of said surface. Each method comprises covalently bonding functional molecules to a metal surface followed by effecting free-radical polymerisation from the functional molecules to build bio-compatible polymer chains.

Figure 5 illustrates a typical surface of a metal article, 501 to be treated in accordance with the present invention. The metal surface essentially comprises an outer layer of metal atoms, 502 and 503 for example which lie below an oxide layer, said oxide layer comprising oxygen atoms such as atom 504 which are bonded to said metal atoms via bonds such as 505 and 506. The exact bonding relationship between the metal atoms and the oxygen atoms will depend on the valency of the metal atoms. Thus in the example shown the valency of said metal atoms is one, such that the electronic shells of said metal atoms are completed via a single bond to an oxygen atom for each respective metal atom.

-13-

Figure 6 details a suitable vinylfunctional silane molecule 601 to be reacted with a metal surface such as for example the metal surface illustrated in Figure 5. As indicated at the respective ends of the vertical carbon chain on said Figure, strictly this Figure illustrates a portion or repeating unit of a silane modified polybutadiene molecule. Such materials have known uses as polymeric coating agents in for example enhancing wet electricals and use-temperature ranges for the wire and cable industry. The essential features of the vinylfunctional silane molecule illustrated are the two silicon atoms 602 and 605 and the double bonds 608 and 609. Silicon atom 602 is bonded to the two alkoxy groups 603 and 604 respectively. Similarly silicon atom 605 is bonded to alkoxy groups 606 and 607 respectively. The alkoxy groups 603, 604, 606 and 607 each include an alkyl group R which may, for example, be a methyl group or an ethyl group. Reaction of groups 603 and 604 etc with a suitable hydrolysing agent such as acetic acid facilitates formation of bonds between silicon atoms, such as atoms 602 and 605 for example and metal surface atoms, such as atoms 502 and 503 illustrated in Figure 5. Also pendant from the hydrocarbon chain are olefinically unsaturated groups 608 and 609 which provide sites from which graft polymerisation can take place initiated by free radicals to build biocompatible polymer chains. A suitable vinylfunctional silane molecule is for example triethoxysilyl-modified polybutadiene as supplied by Fluorochem Limited, UK.

Figure 7 illustrates covalent attachment of the silane molecule detailed in Figure 6 to the metal surface illustrated in Figure 5. The illustration diagrammatically shows silicon atoms 602 and 605 connected to metal via oxygen 701 and 702 via covalent bonds 703 and 704. The illustration shows two covalent bonds attaching each silicon atom to the surface which is preferable for strength and reliability of attachment. However it may be that in some cases a given silicon atom is attached by a single covalent linkage via an oxygen atom to a given metal atom in which case the other bonding site associated with said silicon atom could, for example, be taken up by a hydrogen atom.

The molecule illustrated in Figure 6 is a polymer. Since polymers consist of repeating units all such units or a single unit or several may be bonded to said surface, thus providing covalent bonding to a metal surface at a plurality of locations. Also the

-14-

particular molecule illustrated is seen to have a pair of silicon atoms in a repeating unit and thus in this case a plurality of sites are available for a given repeating unit to bond to a metal surface.

5 The reaction of a vinylfunctional polymer silane with a metallic surface is facilitated (catalysed) by hydrogen ions, as for example supplied from a weak acid such as acetic acid. The reaction is performed in a solvent such as a hydrocarbon solvent e.g. toluene or cyclohexane, since too much water is not suitable for this reaction, water interfering with the desired reaction in that it hydrolyses the "OR" groups, such as groups
10 603 and 604 in Figure 6.

Figure 8 details a suitable polymerisable molecule (vinyl monomer) used to substantially build a polymer chain from the double bonds 608 and 609 shown in Figure 6. The molecule shown is acrylamide and it has an amide group 801 and a double bond
15 802 which can be used for free-radical polymerisation of these molecules from vinylfunctional silane molecules covalently bonded to a metal surface. Such a polymerisable monomer is preferably water soluble, but this solubility is not essential since strictly it depends on the solvents used in the polymerisation reactions and vice versa.

20 Figure 9 details a second polymerisable monomer known as 3-aminopropyl methacrylamide which can build a polymer chain in conjunction with the molecule shown in Figure 8. Free radical polymerisation occurs through the double bond 901, and amine group 902 attached to carbon chain 903 provides a site for additional bonding of a bio-active molecule such as heparin. The carbon chain 903 is seen to consist of three carbon
25 atoms, but other lengths may be suitable and preferable for particular applications.

Figure 10 shows polymerisation at a previously primed metallic surface in accordance with the steps detailed in Figure 4 using the polymerisable molecules detailed in Figures 8 and 9. Polymer chains 1001 and 1002 are seen to be covalently attached to
30 a vinylfunctional silane molecule by covalent bonds 1003 and 1004 respectively. The portion of chain 1001 in braces 1005 is a molecular unit, resulting from incorporation of

-15-

an acrylamide monomer and in braces 1006 is a portion of the polymer chain resulting from incorporation of a 3-aminopropyl methacrylamide monomer. Chains 1001 and 1002 are substantially similar in that they mainly consist of molecular units of the type in braces 1005, with occasional units of the type in braces 1006. The placement of the 3-aminopropyl methacrylamide derived molecular units is random and thus polymer chains 1001 and 1002 will not be identical in this respect. Similarly free-radical polymerisation is itself of a random nature and thus polymer chains 1001 and 1002 are likely to have different lengths. The relative proportions of the polymerisable molecules used may be varied to allow some control over how many portions of a given polymer chain are represented by the molecular unit suitable for attachment of a bio-active molecule. This is important in that when it comes to attachment of a bio-active molecule it may be desirable to minimise the amount of bio-active molecule used. Such minimisation is determined by various factors, one being the number of suitable attachment sites available. On the other hand it may be desirable to maximise the number of sites available for attachment of a bio-active molecule, such as heparin, and thus the relative proportions of the polymerisable molecules may be set to facilitate this. The major factor governing the individual proportions of selected polymerisable molecules is the rate of reaction associated with a given molecule relative to the other polymerisable molecule or molecules. Control over the proportions of the particular polymerisable molecules (one possibly being a bio-active molecule) is particularly important when the process is scaled up in a manufacturing environment where costs of individual chemicals and bio-chemicals used become an important commercial concern.

Figure 11 details the chemical structure of a repeating unit of heparin which is a preferred bio-active molecule for incorporation into or bonding to the polymer chains shown in Figure 10. The repeating unit of this molecule essentially consists of five connected monosaccharide rings such as for example rings 1101 and 1102. The carboxy group 1103 provides means for attachment to certain polymer chains such as chains 1001 and 1002 shown in Figure 10. Specifically carboxy group 1003 covalently bonds to the amine group associated with polymer chain portions such as the molecular unit in braces 1006 in Figure 10.

-16-

Figure 12 illustrates diagrammatically a portion of a metallic surface, functionalised with a covalently bonded vinylfunctional polymeric silane, wherein polymerisation has effected formation of blood-compatible polymer chains in accordance with the steps outlined in Figure 4 and wherein at step 405, incorporation of a bio-active molecule has been effected. In Figure 12 the blood-compatible polymer chains, 1201 and 1202, incorporate heparin molecules, detailed in Figure 11, such as molecule 1203, at various positions along the polymer chains. It should be noted that the Figures in general illustrate the general principles involved, and thus for example in Figure 12 the molecule 1203, as illustrated, is not representative of the size of the molecule involved, a typical heparin molecule being extremely large compared with an acrylamide monomer for example.

The functionalised and polymerised metal surface detailed in Figure 12 is more generally illustrated in Figure 13 wherein metal surface 1301 is preferably a surface of a medical device, said device being used in conjunction with biological material such as blood or blood related products. The surface 1301 has been functionalised by covalently bonding vinylfunctional silane molecules 1302, 1303 and 1304 respectively to said surface. Each respective said vinylfunctional silane molecule is bonded to a polymer chain 1305, 1306 and 1307 respectively, said polymer chains having been built from said vinylfunctional silane molecules via free-radical polymerisation, in accordance with the method illustrated in Figure 4. Certain portions of the chains such as molecular units 1308 and 1310 provide for attachment of bio-active molecules such as heparin molecules 1309 and 1311 respectively. Thus molecular units 1308 and 1310 (detailed in Figure 10 in braces 1006) are attached to a heparin molecule via a bond formed between the amine group 902 shown in Figure 10 and the carboxy group 1103 shown in Figure 11. For illustrative purposes, only one polymer chain such as chain 1305 is shown emanating from any given vinylfunctional silane molecule, such as molecule 1302. In reality many such chains will be emanating from a given vinylfunctional silane molecule, in particular if said molecule is a vinylfunctional polymeric silane as is the case in the preferred embodiment. Furthermore silane molecules of the type detailed in Figure 10 are seen to provide two polymer chains per repeating unit of the polymeric silane. Figure 13 also shows molecules of antithrombin (III), such as the free molecule 1312 and molecule 1313, the latter which

-17-

is illustrated interacting with heparin molecule 1309.

The interaction of antithrombin (III) with blood has been mentioned in the introduction, but further details are provided in Figure 14. The mechanism for the formation of fibrin is complex and involves the sequential activation of coagulation factors such as factor 1401 and 1402 for example. Antithrombin (III) is able to inhibit the sequential mechanism at various points in the reaction sequence. Thus antithrombin (III) may directly inhibit the formation of factor 1403 as indicated by inhibiting process (arrow) 1404. Similarly antithrombin (III) may directly inhibit the conversion of prothrombin to thrombin as indicated by inhibiting process 1405. Thus, the ability of a metallic surface to facilitate and enhance the interaction of antithrombin (III) with said factors is seen to be highly desirable. Use of heparin molecules in accordance with the present invention, generally indicated in Figure 13 is believed to improve the blood-compatibility of a given metal surface through complex formation between covalently bound heparin on said surface and antithrombin (III).

Polymerisation at a metal surface in accordance with the alternative method indicated in Figure 3 is performed using a modified bio-molecule such as heparin macromer. A suitable heparin macromer may be produced in accordance with a method devised by co-inventor K.G. Al-Lamee. This earlier disclosed method is published in the journal "Clinical Materials 10 (1992)", under the title "*Chemical Methods for Improving the Haemocompatibility of Synthetic Polymers*". Figure 15(a) details a modified heparin molecule, produced in accordance with this earlier disclosed method, wherein a heparin molecule 1501 has been modified by covalently bonding to an amine molecule, said amine molecule substantially forming the chemical chain 1502. The covalent bonding between heparin molecule 1501 and chemical chain 1502 is further detailed in Figure 15(b) wherein the relevant covalent bond 1503 is seen to be between a carbon atom on the heparin molecule 1501 and a nitrogen atom on chemical chain 1502.

The molecule of modified heparin illustrated in Figure 15(b) is seen to be a portion, or repeating unit, of a polymer chain. This modified bio-active molecule may be

-18-

reacted in conjunction with a vinyl monomer such as acrylamide in the presence of a functionalised metallic surface, to produce substantially the polymerised surface shown in Figure 12. The molecule illustrated in Figure 15(b) produces polymer chains which are identical to those produced by the method of Figure 3. A functionalised and polymerised metallic surface produced using modified heparin molecules provides a metal surface with substantially the same functionality with regards to blood-compatibility as with the former method using unmodified heparin, said functionality generally being illustrated in Figure 13.

Both of the above described methods for incorporation of heparin onto the surface of a metal could alternatively be applied to other suitable anticoagulants or any other suitable drugs as may be required. Thus, for example, prostaglandin (an anti-platelet agent) or hirudin may be incorporated by similar methods. In the case of heparin, amine groups are necessary to effect suitable bonding, either to a polymer chain already bonded to a given metal surface or to form a suitable modified heparin molecule for incorporation in free-radical polymerisation. In the case of hirudin a carboxyl group, rather than an amine group, is required. Similarly, drugs containing carboxyl groups may be bonded, in accordance with the above methods, via compounds having suitable hydroxyl groups.

Typical metal medical devices requiring improved blood-compatibility are shown in Figures 16(a) to 16(c). Figure 16(a) illustrates a coronary stent made from a metal mesh. Stents are used as inserts in blood vessels to improve the flow of blood through said vessels where a blockage has formed. Traditionally stents are metallic devices that are not biodegradable. Some types of stent are made of criss-crossed wire 1601 which facilitates mechanical flexibility with a vessel wall together with reduced hindrance for endothelialisation around the stent. However problems remain with the use of stents in relation to their poor blood-compatibility properties. The present invention improves the blood-compatibility of the surface of the metal stent and thus provides for a stent which can be left in place in a given blood vessel for a much longer time. Many types of metal stents exist, some being used in the coronary arteries (coronary stents) and others being used peripherally (peripheral stents). Various types exist including for example: coilspring

-19-

stents, thermal shaped memory alloy stents, self expanding steel spiral stents, self expandable stainless steel mesh stents and balloon expanding stents comprising interdigitating coils. All practical metallic stents, such as those listed, are suitable for treatment in accordance with the present invention.

5

Figure 16(b) illustrates a metallic medical device which is used externally to the body. The device illustrated is a heat exchanger wherein blood enters the device through inlet 1602 and is circulated around the internal mechanism 1603 before leaving the device via outlet 1604. The internal mechanism 1603 is placed directly into contact with blood circulating through the device. The present invention facilitates the interaction of the blood with the internal mechanism 1603, thus reducing problems associated with blood coagulation.

10

Figure 16(c) shows a further metallic medical device, a guide wire 1605, as typically used in PTCA. Guide wires of this type are used to insert a balloon into a blood vessel wherein a portion of the vessel wall is restricting blood flow through for example deposited material or plaque. Insertion of a balloon located by a guide wire such as guide wire 1605 is improved in accordance with the present invention. The improvement arises because the guide wire comes into contact with blood and is hindered in its movement due to blood coagulation. The present invention improves the bio- compatibility and lubricity of the surface of the guide wire and thus facilitates the overall surgical process of treating the vessel walls.

15

20

25

30

The present invention is further illustrated by the following examples of laboratory scale treatment of metal surfaces. The examples given relate to stainless steel and Nitinol, but the invention is not limited to the treatment of these two metals. The invention is suitable for treatment of a wide range of metal surfaces. Furthermore the examples given each incorporate usage of a single type of vinylfunctional silane molecule, but in practice several could be used for functionalisation of a given metal surface. The examples illustrate use of monomeric, polymeric and oligomeric vinylfunctional silane molecules. The invention is not limited to improved compatibility of metal articles with blood. It is

-20-

suitable in general for improving the performance of many metal articles with biological materials, another important example being the reduction of bacterial adhesion to certain medical devices.

5 Preparative Example

Production of Heparin Macromers

Heparin macromers were produced by the amidation of carboxyl groups in heparin with amino monomers of the formula set out below, in which $n = 3, 6$ and 12 in aqueous solution with the aid of the condensing agent 1-ethyl-3-(2-dimethylaminopropyl)carbodiimide (EDC) as described by C.H. Bamford and K.G. Al-Lamee, *Chemical Methods for Improving the Haemocompatibility of Synthetic Polymers*, Clinical Materials, **10** (1992), 243-261.



Heparin (1.0g, purchased from Sigma, Dorset, UK) was dissolved in de-ionised water (8.3 ml) and EDC (0.33g was added). The pH was adjusted to between 5 and 6, and after 30 minutes aminopropyl methacrylamide (0.35g) was added. The mixture was maintained at room temperature for 17 hours with mixing by means of a Spiramix roller mixer. The pH was raised to 8 by addition of sodium hydroxide and the solution was then poured into methanol. Heparin macromer (about 0.7g) precipitated and was isolated by filtration. The incorporation of $\text{CH}_2=\text{CH}(\text{CH}_3)$ - groups into the precipitated heparin was confirmed by NMR spectroscopy.

25

The above procedure was repeated using the monomers in which $n = 6$ and $n = 12$ with similar results. Each of the three resulting heparin macromers may be co-polymerised to form a coating on a metal or ceramics substrate having on its surface an oxide film or hydroxyl groups using the procedures described below. However, the monomer in which $n=3$ is preferred on the grounds of availability and efficiency of participation in coupling reactions in aqueous solvents.

-21-

Example 1

Treatment of stainless steel using a siloxane oligomer covalently bonded to the surface

(a) Functionalisation

5

Two samples of stainless steel were cleaned with a solution of sodium bicarbonate (1% w/v) at 60° C for one hour and then washed with hot water. The samples were then dried at room temperature and reacted at room temperature for 2 hours with 1% vinylmethoxysiloxane oligomer (Fluorochem Limited, Old Glossop, Derbyshire, PS078.9) in toluene containing ten drops of acetic acid. The samples were washed successively with methanol and water before being subjected to polymerisation.

(b) Polymerisation

15

A treated surface was formed on the functionalised stainless steel samples by graft polymerisation at room temperature for 3 hours with acrylamide (10% w/v) and heparin macromer (modified heparin, 0.2% w/v) in aqueous medium using sodium thiosulphate (0.1% w/v) and ammonium persulphate (0.1% w/v). The solution was flushed with nitrogen before the graft polymerisation was carried out. The samples were then carefully washed with water before being biologically tested using the APTT-FS test.

(c) Activated Partial Thromboplastin Time-Fs (APTT-FS)

The APTT test has been widely used to monitor the effectiveness of heparin, where the clotting time is prolonged in proportion to the amount of available heparin. In the present test, a small sample of stainless steel treated with heparin, as described above, was placed in a test tube containing 200 micro-litres of plasma and incubated for one minute at 37°C. The size of the stainless steel sample used was 4mm x 4mm. Following incubation, 200 micro-litres of APTT-FS agent were added into the test tube containing the plasma and the test sample, and then incubated for a further 3 minutes at 37°C. Following this incubation period, 200 micro-litres of calcium chloride solution (20mM)

-22-

were added into the reaction mixture and simultaneously a timer was started and the clotting time recorded. The APTT results are shown in the table below:

5	Sample	Mean Value of Clotting Time (seconds)
	Plasma control	37
	Untreated stainless steel	9
10	Heparin covalently coupled, hydrophilic stainless steel	60

(d) *In Vitro* bovine blood-flow test

Bovine blood with an ACT of 200 s was circulated for 6 hours over untreated and heparin treated stainless steel using a peristaltic pump and a circulation rate of 3.5 L/min. After the circulation period the stainless steel samples were removed and washed with saline. They were then fixed with glutaraldehyde (2%) and examined by scanning electron microscopy (SEM). A sample of the re-circulated blood was tested for its ACT and exhibited no significant change from the pre-test value. A SEM micrograph of the untreated sample (Fig. 17a) showed cell and fibrin deposition onto the surface, whereas no such deposition was apparent on the hydrophilic treated and heparinised sample produced as described above (Fig 17 b). These results indicate that the present treatment gives stainless steel a significantly better haemocompatibility than the untreated material.

(e) Stability of heparin on the surface

The ability of heparin to remain stable and active on a treated surface was investigated by incubating the treated metal in saline at 37°C for a week. An APTT test was then carried out which demonstrated that the covalently attached heparin was stable and retained its biological activity.

Another treated sample was allowed to remain in contact with blood for an hour so that a clot formed and became attached to the metal surface. The clot was removed by rubbing and the sample was washed under tap water. An APTT test was carried out,

-23-

which revealed that the clotting time remained longer than in an untreated sample.

(f) Spectroscopic detection

An untreated sample and samples having copolymerised material with different ratios M/H of monomer to heparin macromer were prepared using the general procedure described above. The samples were extensively eluted to remove unbound and unreacted chemical species. The atomic ratios of C/O, N/O and S/O were measured by X-ray photoelectron spectroscopy (XPS) with the following results

10

Sample	M/H	C/O	N/O	S/O
Untreated stainless steel (control)	-	0.56	0.00	0.00
Treated stainless steel	1:1	1.41	0.06	0.04
Treated stainless steel	2:1	1.64	0.14	0.05

15

Example 2

Coating a nickel/titanium alloy using a silane covalently bonded to the surface

20

(a) Functionalisation

Two samples of Nitinol were cleaned with a solution of sodium bicarbonate (1% w/v) at 60°C for one hour and then washed with hot water. The samples were then dried at room temperature before being reacted at room temperature for 12 hours with 3-(trimethoxysilyl)propyl methacrylate (Aldrich Chemical Company; 10% in hexane containing ten drops of acetic acid). The samples were washed with methanol and water successively before being subjected to polymerisation.

25

30

-24-

(b) Polymerisation

A treated surface was formed on the functionalised Nitinol samples by graft polymerisation at room temperature for 3 hours with acrylamide (10% w/v) and heparin macromer (modified heparin, 0.2% w/v) in aqueous medium using sodium thiosulphate (0.1% w/v) and ammonium persulphate (0.1% w/v). The solution was flushed with nitrogen before the graft polymerisation was carried out. The samples were then carefully washed with water before biologically tested using the APTT-FS test.

(c) Activated Partial Thromoplastin Time-FS

Sample	Mean Value of Clotting Time (seconds)
Plasma control	35
Untreated stainless steel	8
Heparin covalently coupled, hydrophilic stainless steel	61

Example 3

Formation of covalently bound material and subsequent attachment of heparin.

(a) Functionalisation

Two samples of stainless steel were cleaned with a solution of sodium bicarbonate (1% w/v) at 60° C for one hour and then washed carefully with hot water. The samples were then dried at room temperature before being reacted with 1% Triethoxysilyl-modified polybutadiene (Fluorochem Limited, PS078.6) in toluene containing ten drops of acetic acid at room temperature for 2 hours. The samples were washed with methanol and water respectively before being subjected to polymerisation.

-25-

(b) Polymerisation

A treated surface was formed on the functionalised stainless steel samples by graft polymerisation at room temperature for 3 hours with acrylamide (10% w/v) and 3-aminopropyl methacrylamide (0.1% w/v) heparin macromer in aqueous medium using sodium thiosulphate (0.1% w/v) and ammonium persulphate (0.1% w/v). The solution was flushed with nitrogen before the graft polymerisation was carried out. The samples were then carefully washed with water before being coupled with 0.1% unmodified heparin (Fluka Chemical Company), and 0.03% w/v 1-ethyl-3-(3-dimethyl amino propyl) carbodiimide hydrochloride (pH 4-5) at room temperature for 6 hours. The samples were then washed carefully with water before biologically tested using APTT-FS.

(c) Activated Partial Thromboplastin Time-FS

Sample	Mean Value of Clotting Time (seconds)
Plasma control	34
Untreated stainless steel	10
Heparin covalently coupled, hydrophilic stainless steel	73

Example 4**Attachment of additional compounds to metallic stents**

Stainless steel stents were functionalised with triethoxy siloxane modified polybutadiene (Fluorochem) as described in Example 3 above.

A treated surface was then prepared on some of them by copolymerising acrylamide (10% w/v) and dipyrindamole (Persantin) monomethacrylate ester (5% w/v) using azo-cyano valeric acid as initiator. The solution was flushed with nitrogen, and polymerisation was carried out at 60°C for three hours. The samples were then washed extensively with water and methanol sequentially.

-26-

In an alternative procedure, the treated surface was prepared as described above except that there was additionally present as co-monomer heparin macromer (modified heparin, 0.2% w/v).

5 Stents made by each of the above two procedures were dipped in solutions of vascular endothelial growth factor (VEGF, Sigma, stock solution, 80 ng/ml) which became ionically attached to the coating.

10 A further group of the stents made by the above two procedures was dipped into human platelet GPIIbIIIa (Sigma, stock solution, 80 ng/ml) which became ionically attached.

15 Stents made as above can be sterilised e.g. using ethylene oxide and packed in a sterility-maintaining container. On implantation, the stents exhibit good haemocompatibility and their coating encourages growth of endothelial cells.

Example 5

Formation of covalently bonded material on the surface of glass

20 A glass tube was reacted at room temperature for 30 minutes with 1% w/v triethoxysilyl-modified polybutadiene (Fluorochem Ltd) in toluene containing ten drops of acetic acid. The tube was then washed with methanol and water.

25 A graft polymer was then formed on the surface of the resulting functionalised tube using acrylamide (5% w/v) in an aqueous medium which was flushed with nitrogen. The reaction was carried out at room temperature for two hours with continued flushing with nitrogen and using sodium thiosulphate (0.1% w/v) and ammonium persulphate (0.1% w/v). A very slippery surface coating was formed which was resistant to prolonged washing with hot water.

30

- 27 -

Claims

1. A method of treating a metal, glass or ceramics article having at its surface oxide or hydroxide to
5 enhance the bio-compatibility and/or physical characteristics of the surface, said method comprising the steps of

covalently bonding to said surface by means of a catalyst functional molecules each of which has at least one
10 alkoxy silane group which can form at least one first covalent bond by reaction with the oxide or hydroxide of said surface and at least one other group which can participate in free-radical polymerisation; and

effecting free-radical polymerisation from said
15 functional molecules to build bio-compatible and/or hydrophilic polymer chains.

2. The method of claim 1, wherein said article is a coronary stent (endovascular prosthesis), peripheral
20 stent, heat exchanger for use in conjunction with biological material, guide wire for use in angioplasty, artificial heart valve, device for storage and/or transfer of biological material, or other medical device.

25 3. The method of claim 2, wherein said article is one of the following stents:

a coil spring stent;




- 28 -

a thermal shaped memory alloy stent;
a self-expanding steel spiral stent;
a self-expandable stainless steel mesh stent;
a balloon expanding stent comprising inter-
5 digitating coils.

4. The method of any preceding claim, wherein the
article is of stainless steel or nitinol.

10 5. The method of any preceding claim, wherein said
functional molecules have olefinically unsaturated
groups.

6. The method of claim 5, wherein the functional
15 molecules are of any of the formulae:



20

wherein R^1 represents a hydrogen atom or an alkyl group,
 R^2 , R^3 and R^4 represent an alkyl group and n is 0 or is
a positive integer.

25 7. The method of claim 6, wherein R^1 represents
hydrogen, methyl or ethyl and R^2 , R^3 and R^4 represent

- 29 -

methyl or ethyl and the value of n is from 0 to 6.

8. The method of claim 7, wherein the functional molecule is a trialkoxysilane.

5

9. The method of claim 5, wherein the functional molecules comprise a $[-Si-O-]_n$ chain having alkoxy groups directly attached to the silicon atoms and having olefinically unsaturated groups attached directly or via linking groups to the silicon atoms.

10

10. The method of claim 9, wherein the functional molecules have vinyl and alkoxy groups attached to the silicon atoms of the chain.

15

11. The method of claim 5, wherein the functional molecules have:

an oligomeric or polymeric chain of carbon atoms which may include nitrogen or oxygen atoms;

20

one or more alkoxysilane or alkylalkoxysilane groups attached to the chain for forming covalent bonds with oxide or hydroxide of the surface; and

one or more olefinically unsaturated groups which can participate in free radical polymerisation.

25

12. The method of claim 9, wherein the functional molecules have trialkoxysilane groups.

- 30 -

13. The method of claim 5, wherein said functional molecules include one or more of:

3-(trimethoxysilyl) propyl methacrylate;

5 vinylmethoxysiloxane oligomer;

diethoxymethylsilyl-modified polybutadiene

triethoxysilyl-modified polybutadiene.

14. The method of any preceding claim, wherein said
10 free-radical polymerisation includes polymerising a plurality of types of polymerisable molecules.

15. The method of any preceding claim, wherein said polymer chains include molecular units derived from
15 acrylamide.

16. The method of any preceding claim, wherein at least one type of said polymerisable molecule provide means for bonding to a bio-active molecule.

20

17. The method of claim 16, wherein said bonding means is an amine group.

18. The method of claim 17 wherein said amine group is
25 provided by 3-aminopropyl methacrylamide.

19. The method of claim 16, wherein said bonding means

- 31 -

is a carboxyl group.

20. The method of claim 16, wherein said bonding means is a hydroxyl group.

5

21. The method according to claim 14, wherein at least one type of said polymerisable molecules is bio-active molecule which has been modified to contain a polymerisable group.

10

22. The method of claim 16 or 21, wherein said bio-active molecule is an anticoagulant or anti-platelet agent.

15 23. The method of claim 22, wherein said anticoagulant is heparin.

24. The method of claim 22, wherein said anticoagulant is hirudin.

20

25. The method of claim 22, wherein said anti-platelet agent is prostaglandin or an analog thereof.

26. The method of any preceding claim, wherein said
25 treatment of a metal surface is conducted substantially at room temperature.

- 32 -

27. The method of any preceding claim, comprising the additional step of sterilising the article and optionally packing the article in a sterility-preserving container or wrapper..

5

28. A bio-compatible metal, glass or ceramics article comprising residues derived from functional molecules covalently bonded to the surface of said article and bio-compatible polymer chains covalently bonded to said
10 functional molecule residues.

29. The article of claim 28, wherein said functional molecule residues are derived from vinylfunctional silane molecules.

15

30. The article of claim 29, wherein said functional molecule residues are derived from trialkoxysilane-containing molecules.

20 31. The article of claim 29 or 30, wherein said vinylfunctional silane molecules are polymers comprising a plurality of repeating units.

32. The article of claim 31, wherein said polymers are
25 bonded to said surface at a plurality of locations.

33. The article of claim 32, wherein said repeating

- 33 -

units are bonded to said surface at a plurality of locations.

34. The article of claim 28, wherein said
5 vinylfunctional silane molecules include one or more of:
vinylmethoxysiloxane oligomer,
3-(trimethoxysilyl) propyl methacrylate,
diethoxymethylsilyl-modified polybutadiene, or
triethoxysilyl-modified polybutadiene.

10

35. The article of any of claims 28-34, wherein said
bio-compatible chains are compatible with blood or blood
related products.

15 36. The article of any of claims 28-35 wherein said bio-
compatible polymer chains are hydrophilic.

37. The article of any of claims 28-36, wherein said
polymer chains consist of a plurality of types of
20 molecular units.

38. The article of any of claims 28-37, wherein said
molecular units include units derived from acrylamide.

25 39. The article of any of claims 28-38, wherein said
molecular units include units derived from 3-aminopropyl
methacrylamide.

- 34 -

40. The article of any of claims 31 to 39, wherein at least one type of said molecular unit includes a covalently bonded bio-active molecule.

5

41. The article of claim 40, wherein said bio-active molecule is a blood anticoagulant or an anti-platelet agent.

10 42. The of claims 40 or 41, wherein said bio-active molecule is heparin or a heparin derived molecule.

43. The article according to claims 41 or 42, wherein said bio-active molecule is prostaglandin or a molecule
15 derived therefrom.

44. The article of any claims 41-43, wherein said bio-active molecule is hirudin or a molecule derived therefrom.

20

45. The article of any of claims 28 to 44, which is a coronary stent (endovascular prosthesis), peripheral stent, heat exchanger used in conjunction with biological material, guide wire used in angioplasty,
25 artificial heart valve, device is used for storage and/or transfer of biological material or other medical device.

- 35 -

46. The article of any of claims 28 to 44, which is one of the following:

a coil spring stent;

5 a thermal shaped memory alloy stent;

a self-expanding steel spiral stent;

a self-expandable stainless steel mesh stent;

a balloon expanding stent comprising inter-digitating coils.

10




Figure 1




Figure 2




Figure 3




Figure 4

105




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10




Figure 11




Figure 12





Figure 14






Figure 16 a




Figure 16 b




Figure 16 c

Figure 17a



Figure 17b






Figure 1




Figure 2

103




Figure 3




Figure 4

105




Figure 5




Figure 6




Figure 7




Figure 8




Figure 9




Figure 10




Figure 11




Figure 12




Figure 13




Figure 14

Figure 15 a




Figure 15 b




Figure 16 a




Figure 16 b





Figure 16 c

Figure 17a



Figure 17b



BNSDOCID: <WO 9855162A3_1_>

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 98/01609

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61L31/00 A61L33/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 356 433 A (ROWLAND STEPHEN M ET AL) 18 October 1994 cited in the application	1-4, 13, 15-27, 34-45
Y	see column 4, line 22 - column 6, line 8	5-12, 14, 28-33
Y	WO 91 17046 A (UNIV NEW YORK) 14 November 1991 see claims 1, 3, 4	5-12, 14, 28-33
A	US 5 344 455 A (KEOGH JAMES R ET AL) 6 September 1994 see column 2, line 3 - line 21	14, 17, 37, 38

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance
"E" earlier document but published on or after the international filing date
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
"O" document referring to an oral disclosure, use, exhibition or other means
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
"&" document member of the same patent family

Date of the actual completion of the international search

6 January 1999

Date of mailing of the international search report

14/01/1999

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Heck, G

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/01609

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 5356433 A	18-10-1994	NONE	
WO 9117046 A	14-11-1991	US 5112640 A	12-05-1992
		AU 7794491 A	27-11-1991
		CA 2062802 A	05-11-1991
		EP 0485548 A	20-05-1992
		JP 5501130 T	04-03-1993
		US 5224958 A	06-07-1993
US 5344455 A	06-09-1994	EP 0596615 A	11-05-1994
		JP 2691854 B	17-12-1997
		JP 7016291 A	20-01-1995
		US 5476509 A	19-12-1995
		US 5545213 A	13-08-1996